

Morris Coupling Company

TEMPERATURE MAX LIMITATIONS OF GASKET MATERIAL FOR MORRIS COMPRESSION COUPLINGS

	DUROMETER	TEMPERATURE MAX		CONTINUOUS TEMPERATURE
		F°	C°	
GUM RUBBER	40	200°	93°	180° F
RED RUBBER	75	210°	98°	180° F
BLACK NEOPRENE	60	200°	93°	189° F
WHITE NEOPRENE*	60	200°	82°	180° F
EPDM BLACK	60	275°	135°	250° F
WHITE EPDM	60	250°	121°	180° F
VITON	70	600°	315°	450° F
RED SILICONE	60	500°	260°	450° F
BLUE SILICONE (Metal detectable)	60	500°	260°	450° F
NON-ASBESTOS 3700		700°	370°	400° F
NITRILE	60	225°	107°	200° F

* FDA Approved



2240 W. 15th St. • Erie, PA 16505 • Phone: 814-459-1741
Toll Free: 1-800/426-1579 • Fax: 1-800/545-1399
Website: www.morriscoupling.com • E-mail: sales@morriscoupling.com